

DETAILS & COMPOSITION

Suitable Environment	Dry floors with an occasional spill. Avoid constant pooling fluids. Clean with a neutral PH cleaner.
Categories & Applications	Non-Conductive
Customization Options	C1 - Custom Length
Solid or Drainage	Solid
Material	PVC
Recycled	<10%
Warranty	1 Year

TEST RESULTS

Property	Test / Result
Flammability	ASTM D178-01 / Maximum 12.7 mm after 30sec.
Taber Abrasion	ASTM D 3884 / 1% loss
Temperature Range	Not Available
Coefficient of Friction	ASTM F1677 / Dry: COF =.68 / Wet: COF = .32
Compression Deflection	Not Available
Tear Strength	ASTM D412 Die C results: 1212 psi
ESD Rating	Not Applicable
Dielectric Strength	Surface conforms to ANSI/ASTM D178 01, Type II, Class 2: 30,000 volts. (Recommended Max Usage up to 17,000 volts)